

# Demireller

Madencilik · Mining

Bauxite Product Groups	Top Grade	High Grade	Regular Grade	Cement Grade
Al <sub>2</sub> O <sub>3</sub> (%) (min)	57	54	52	48
SiO <sub>2</sub> (%) (maks)	4	6	8	10-12
Fe <sub>2</sub> O <sub>3</sub> (%)	22-27	22-27	22-27	22-27
TiO <sub>2</sub> (%)	2,5-3,5	2,5-3,5	2,5-3,5	2,5-3,5
CaO (%)	1-3	1-3	1-3	1-3
Moisture (%)	2-6	2-6	2-6	2-6
Loss of ignition(LOI)	10-12	10-12	10-12	10-12
Loading Ports	Gemlik, Milas	Güllük, Mersin	Güllük, Mersin	Güllük, Mersin, Gemlik